

BLANK PAGE



Indian Standard METHODS OF TEST FOR INTERNAL PRESSURE RESISTANCE OF GLASS CONTAINERS

UDC 621:798:147:666:171:620:162:4



@ Copyright 1983

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

Indian Standard

METHODS OF TEST FOR INTERNAL PRESSURE RESISTANCE OF GLASS CONTAINERS

Glass Containers Sectional Committee, MCPD 13

Chairman

Representing

SHRI C. K. SOMANY

Hindustan National Glass & Industries Ltd. Calcutta

Members

SHRI A. C. JAIN (Alternate to Shri C. K. Somany)

SHRI C. G. AMIN

SHRI R. P. PATEL (Alternate)

SHRI N. G. BASAK

SHRI I. K. KAPOOR (Alternate) SHRI M. BHATIA

SHRI A. S. DESAI (Alternate) DR B. K. CHAKRABORTY CHIEF CHEMIST

DEPUTY CHIEF CHEMIST (Alternate)

SHRI DAYA NAND

SHRI J. P. GANATRA

DIRECTOR

Alembic Glass Industries Ltd. Vadodara

Directorate General of Technical Development, New Delhi

Directorate of Food (Ministry of Agriculture), New Delhi

National Dairy Development Board, Anand Department of Revenue (Ministry Finance), New Delhi

All India Food Preservers' Association (Regd), New Delhi

Directorate of Weights & Measures (Ministry of Civil Supplies), New Delhi

DEPUTY DIRECTOR (W & M) (Alternate) Directorate of Food and Drugs Control Administration, Ahmadabad

SHRI J. G. TRIVEDI (Alternate) SHRI R. S. GROVER

SHRI S. K. GUPTA (Alternate)

SHRI J. K. KHOSLA

SHRI N. SREERAMULU (Alternate)

Jg Glass Industries Limited, Pune

Metal Box India Ltd, Calcutta

(Continued on page 2)

@ Copyright 1983 INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

Members

Representing

SHRI S. V. KRISHNASWAMY SHRI J. MUKERJI Wimco Limited, Bombay

Central Glass and Ceramic Research Institute (CSIR). Calcutta

DR K. P. SRIVASTAVA (Alternate)

SHRI K. H. PARIKH Vazir Glass Works Ltd, Bombay

SHRI S. D. MARKETKAR (Alternate)

SHRI B. K. RAMACHANDANI The Mahalakshmi Glass Works Pvt Ltd,
Bombay

SHRI K. M. SAMTANI (Alternate)

SHRI L. K. SHAH Herbertsons Limited, Bombay

Shri M. S. Parikh (Alternate) Shri N. D. Shetty

All India Glass Manufacturers' Federation, New Delhi

SHRI H. K. UPADHYAYA SHRI P. S. DAS, Director (MCPD) Larsen & Toubro Limited, Bomby Director General, ISI (Ex-officio Member)

Secretary

SHRI A. R. GULATI Deputy Director (MCPD), ISI

Indian Standard

METHODS OF TEST FOR INTERNAL PRESSURE RESISTANCE OF GLASS CONTAINERS

0. FOREWORD

- 0.1 This Indian Standard was adopted by the Indian Standards Institution on 30 March 1983, after the draft finalized by the Glass Containers Sectional Committee had been approved by the Marine, Cargo Movement and Packaging Division Council.
- 0.2 The methods cover the determination of the breaking strength of glass containers when subjected to internal pressure. The methods are intended to determine the pressure strength of containers manufactured to contain products reasonably expected to develop a sustained pressure of 140 kPa or above.
- 0.2.1 The test pressure limits for the containers have been specified in the relevant specifications on the glass bottles for aerated drinks and glass beer bottles.
- 0.3 The methods detailed here are based on the ISO/DIS 7458 'Glass container internal pressure resistance Test method', issued by the International Organization for Standardization (ISO).

1. SCOPE

1.1 This standard specifies the test methods for the determination of the internal pressure resistance of glass containers.

2. SAMPLING

2.1 The test is performed on a predetermined number of containers. The containers used for the test shall not have been subjected to any other mechanical or thermal test which could adversely affect their internal pressure resistance.

3. METHODS OF TEST

3.1 Method A — Application of Uniform Internal Pressure for a Predetermined Period

3.1.1 Apparatus

- 3.1.1.1 The apparatus shall comply with the following principles:
 - a) The container to be tested shall be held in such a manner that it is suspended by the finish;
 - b) There shall be a resilient seal between the sealing surface and the pressure head to retain the pressuring medium during the test; and
 - c) There shall be means of applying fluid pressure to a predetermined level at a rate of 1±0.2 MPa/s for maintaining that pressure constant during the test.

3.1.2 Procedure

- 3.1.2.1 Allow the containers to achieve ambient temperature and then fill them with water at a temperature $\pm 5^{\circ}$ C from ambient.
- 3.1.2.2 Use one of the following test procedures, depending upon the purpose of the test:
 - a) Pass Test Apply the internal test pressure to the predetermined level and hold it constant for 60±2 s or for a different period, provided that the apparatus has the means for correcting the pressure values to those which would be obtained for a 60 s test.
 - b) Progressive Test Continue the test described in 3.1.2.2(a) by increasing the pressure by increments of 0.1 or 0.2 MPa until 50 percent or/and 100 percent of containers are broken.

3.1.3 Test Report

- 3.1.3.1 The test report shall include the following:
 - a) Number of this Indian Standard;
 - b) The sample size and method of sampling;

- c) Number of containers from each mould included in the sample;
- d) Type of test, that is, 3.1.2.2 (a) or (b);
- e) Test results:
 - i) For the 'pass test' in accordance with 3.1.2.2 (a)

Pressure used and number of containers that failed in the test with the respective pressure.

ii) For the 'progressive test' in accordance with 3.1.2.2 (b)

Pressure at which first failure occurred and number of containers that failed at that pressure;

Pressure required to break the predetermined percentage of the sample, expressed to the nearest 0.01 MPa; and Mean breaking pressure and the standard deviation.

3.2 Method B — Application of Internal Pressure Increasing at a Predetermined Constant Rate

3.2.1 Apparatus

- 3.2.1.1 The apparatus shall comply with the following principles:
 - a) The bottle to be tested shall be held in such a manner that it is suspended by the finish.
- b) There shall be a resilient seal between the sealing surface and the pressure head to retain the pressurizing medium during the test.
- c) There shall be means of applying fluid pressure increasing at a rate of 1-0.2 MPa/s until the container fails or a predetermined level is reached. The rate of increase of pressure shall be reproducible; to ± 2 percent.
- d) The apparatus shall include means of indicating the pressure level at which the container failed or the maximum pressure reached during the test.
- e) The apparatus shall include means of indicating the relationship between the constant rate and fixed duration test.

3.2.2 Procedure

3.2.2.1 Allow the containers to achieve ambient temperature and then fill them with water at a temperature \pm 5°C from ambient.

- 3.2.2.2 Use one of the following test procedures, depending upon the purpose of the test:
 - a) Pass Test Increase the internal test pressure at a rate of 1—0.2 MPa/s until a predetermined level of pressure has been reached.
 - b) Progressive Test Increase the internal test pressure at a rate of 1-0.2 MPa/s until each container breaks.

3.2.3 Test Report

- 3.2.3.1 The report shall include the following:
 - a) Number of this Indian Standard;
 - b) The sample size and method of sampling;
 - c) Number of containers from each mould included in the sample;
 - d) Type of test, that is, 3.2.2.2 (a) or (b);
 - e) Test results:
 - i) For the 'Pass Test' in accordance with 3.2.2.2 (a)

Pressure used and the number of containers that failed in the test with the respective pressure.

ii) For the 'Progressive Test' in accordance with 3.2.2.2 (b)

Pressure level at which first failure occured.

Number of containers that failed at that pressure.

Pressure required to break the predetermined percentage of the sample, expressed to the nearest 0.01 MPa.

Mean breaking pressure and the standard deviation.